

Application No. 10/702,440
Amendment dated May 9, 2005
Response to Office Action dated February 10, 2005

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (currently amended) A photothermographic material containing, on a substrate, at least a photosensitive silver halide having an average particle size of 5 nm to 40 nm, a non-photosensitive organic silver salt comprising silver behenate in an amount of 40 mol% to 99 mol%, a reducing agent and a binder, in which the total silver iodide content of the photosensitive silver halide is 40 mol% to or more and 100 mol% or less, and the coating amount of photosensitive silver halide in terms of an amount of silver is ~~0.0005~~ 0.005 g/m² to or more and 0.4 0.05 g/m² or less wherein the photosensitive silver halide is formed in a state where the non-photosensitive organic salt is not present.

2. (cancelled)

3. (currently amended) A photothermographic material according to claim 1, wherein the total silver iodide content is 90 mol% ~~or more and~~ to 100 mol% ~~or less~~.

4. (cancelled)


Application No. 10/702,440
Amendment dated May 9, 2005
Response to Office Action dated February 10, 2005

5. (cancelled)

6. (cancelled)

7. (original) A photothermographic material according to claim 1, wherein the reducing agent contains a compound represented by the general formula (R):

General formula (R)




in which R¹¹ and R^{11'} each represents independently an alkyl group of 1 to 20 carbon atoms, R¹² and R^{12'} each represents independently an alkyl group of 1 to 20 carbon atoms, L represents an -S- group or -CHR¹³- group, R¹³ represents a hydrogen atom or an alkyl group of 1 to 20 carbon atoms, and X¹ and X^{1'} each represents independently a hydrogen atom or a group capable of substitution on a benzene ring.

8. (original) A photothermographic material according to claim 7, wherein R¹¹ and R^{11'} in the general formula (R) each represents independently a secondary or tertiary alkyl group of 3 to 15 carbon atoms.

Application No. 10/702,440
Amendment dated May 9, 2005
Response to Office Action dated February 10, 2005

9. (original) A photothermographic material according to claim 1, which further comprising a compound represented by the following general formula (H):

General formula (H)



in which Q represents an alkyl group, aryl group or heterocyclic group, Y represents a bivalent connection group, N represents 0 or 1, Z_1 and Z_2 each represents a halogen atom, and X represents a hydrogen atom or an electron attractive group.

10. (original) An image forming method for a photothermographic material which comprises exposing a photothermographic material according to claims 1 by using a semiconductor laser having an emission peak intensity at a wavelength of from 350 nm to 450 nm as a light source.

11. (cancelled)

12. (currently amended) A photothermographic material according to claim 1, wherein the average γ -phase ratio of the photosensitive silver halide is 5 mol% ~~or more~~ and to 90 mol% ~~or less~~.

13. (currently amended) A photothermographic material according to claim 1, wherein the average γ -phase ratio of the photosensitive silver halide is 25 mol% ~~or more~~ and to 50 mol% ~~or less~~.

Application No. 10/702,440
Amendment dated May 9, 2005
Response to Office Action dated February 10, 2005

14. (original) A photothermographic material according to claim 1, further comprising a compound in which a one-electron oxidant formed by one-electron oxidation can release one electron or more electrons.


15. (cancelled)

16. (currently amended) A photothermographic material according to claim 1, wherein the non-photosensitive organic silver salt contains silver behenate by in an amount of 65 mol% ~~or more and to~~ 85 mol% ~~or less~~.

17. (original) A photothermographic material according to claim 1, further comprising a development accelerator.

18. (original) A photothermographic material according to claim 1, further comprising a compound represented by the following general formula (D):

General formula (D)



in which R²¹ to R²³ each represents independently an alkyl group, aryl group, alkoxy group, aryloxy group, amino group or heterocyclic group.

Application No. 10/702,440
Amendment dated May 9, 2005
Response to Office Action dated February 10, 2005

19. (original) An image forming method for a photothermographic material according to claim 10, wherein the exposure illuminance of the semiconductor laser is 1 mW/mm² or more.

20. (currently amended) An image forming method for the photothermographic material according to claim 10, wherein the exposure illuminance of the semiconductor laser is 10 mW/mm² ~~or more and~~ to 50 mW/mm² ~~or less~~.